

## The Delphion Integrated View

Get Now: 

PDF | More choices...

Tools: Add to Work File: Create new Wo

Vi w: INPADOC | Jump to: Top

Go to: Derwent...

□ Email

**PTitle:** JP2002110124A2: SEPARATOR FOR SEALED LEAD-ACID BATTER)

P Country: JP Japan

**%** Kind: A2 Document Laid open to Public inspection

PInventor: KAKIZAKI YOSHINOBU;

MATSUNAMI TAKAAKI; KAWACHI MASAHIRO;

**MITANI TAKUO**;

**PAssignee:** NIPPON MUKI CO LTD

News, Profiles, Stocks and More about this company

Published / Filed: 2002-04-12 / 2000-09-28

PApplication JP2000000295765

Number:

**PIPC Code:** H01M 2/16;

Priority Number: 2000-09-28 JP2000000295765

**PAbstract:** 

PROBLEM TO BE SOLVED: To eliminate the occurrence of a fracture in a bending part and preclude deterioration due to weathering phenomenon found in an ultrafine glass fiber by increasing durability and preventing deterioration of a separator for a sealed lead-acid battery.

SOLUTION: The separator for a sealed lead-acid battery contains, as a main body, glass composition including, by mass%, SiO2 of 63.0-66.0, Al2O3 of 4.0-5.1, B2O3 of 5.5-7.5, Na2O+K2O of 14.6-18.2, MgO of 2.7-3.7, CaO of 3.7-5.3, BaO of 0-0.3, and 0-0.2 others, which constitutes an ultrafine glass fiber.

COPYRIGHT: (C)2002, JPO

**POther Abstract** CHEMABS 136(19)297405K DERABS C2002-512116

Info:









this for the Gallery...

© 1997-2003 Thomson Delphion

Research Subscriptions | Privacy Policy | Terms & Conditions | Site Map | Contact U: